



# KÖSTER PUR Membrane Adhesive

## Solvent free, moisture curing polyurethane for strip or full surface adhesion of KÖSTER TPO F and KÖSTER ECB F Membranes

### Features

KÖSTER PUR Membrane Adhesive is a ready to use, one component, solvent free polyurethane for strip and full surface adhesion of KÖSTER fleece backed TPO and ECB membranes.

roof surface is in accordance with

DIN EN 1991-1-4/NA:2010:12. A free installation plan can be obtained from KÖSTER BAUCHMIE AG. Please fill out the required wind load calculation form.

### Technical Data

Color	yellow / brown
Viscosity at + 20 °C	approx. 7,000 mPa * s
Flash point	greater than + 100 °C
Density at + 20 °C	approx. 1.12 g / cm <sup>3</sup>
Working temperature	+ 5 °C to + 40 °C
Pot life	approx. 20 min.
Setting time	2 to 6 hours

### Consumption according to roof surface type

Roof area	Number of strips per m	Adhesive consumption
Inner area	4	ca. 160 g/m <sup>2</sup>
Inner edge area	5	ca. 200 g/m <sup>2</sup>
Outer edge area	6	ca. 240 g/m <sup>2</sup>
Corner area	8	ca. 320 g/m <sup>2</sup>

### Fields of Application

KÖSTER PUR Membrane Adhesive is used for strip bonding and full area adhesion of KÖSTER ECB F and KÖSTER TPO F Membranes.

Strip width approx. 2 cm, (approx. 40 g/m). For full surface adhesion installation, a consumption of approx. 400 g/m<sup>2</sup> to 450 g/m<sup>2</sup> is calculated.

### Substrate

The substrate must be sound and solid as well as free of bond inhibiting agents such as dust, grease, and oil. It may be necessary to prime the substrate with KÖSTER Bitumen Primer to facilitate suitable bonding characteristics.

### General Information:

- concrete, aerated concrete, bituminous membranes etc.
- The surface has to be sound and solid, free of water and clean
- Application temperature: + 5 °C to + 40 °C
- Use only as much adhesive as can be applied in 5 minutes
- Membranes are rolled out and pressed down
- Pressing down the membranes is required a second time after 30 minutes
- Setting time: 2 to 6 hours
- In originally sealed packages stored in cool conditions, the material can be stored for min. 9 months

Suitable substrates include:

- Concrete
- Foamed concrete
- Mineralized bituminous roofing membranes
- Polyurethane foam with lamination
- Polystyrene foam
- Mineral wool insulation with lamination

**Important note:** Uncoated and laminated insulation materials must be approved by the manufacturer for bonding.

### Consumption

160 - 450 g / m<sup>2</sup>

### Application

Installation shall be performed according to the KÖSTER Installation Instructions. KÖSTER Membrane Adhesive can be poured directly from the packaging or applied with a multi-bead adhesive application device.

### Cleaning

Clean fresh material with KÖSTER PUR Cleaner. Reacted material must be mechanically removed.

Do not apply more adhesive than can be covered in 5 minutes.

### Packaging

RT 101 006 6.5 kg jerrycan

Press the membrane down with a weighted roller to evenly disperse the adhesive.

### Storage

In originally sealed packages it can be stored for a minimum of 6 months.

Check the spread by lifting the edge of a membrane. This control is especially important on uneven surfaces.

### Safety

Wear protective goggles and appropriate Personal Protective Equipment when processing the material. Observe all governmental, state, and local safety regulations when processing the material.

### KÖSTER PUR Membrane Adhesive Consumption Table

The adhesive consumption depends on the type of installation. For strip adhesion installation the consumption is approximately 200 g/m<sup>2</sup> to 250 g/m<sup>2</sup>, for full surface adhesion approx. 450 g/m<sup>2</sup>. The division of the

### Related products

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER PUR Cleaner

Prod. code IN 900  
010

KÖSTER ECB 2.0 F

Prod. code RE 820 F

KÖSTER TPO 1.6 F

Prod. code RT 816 F

KÖSTER TPO 1.8 F

Prod. code RT 818 F

KÖSTER TPO 2.0 F

Prod. code RT 820 F

KÖSTER TPO 2.0 U

Prod. code RT 820 U

KÖSTER Bitumen Primer

Prod. code W 110

010

KÖSTER Spatula

Prod. code X 987

001

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

**KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • [info@koester.eu](mailto:info@koester.eu) • [www.koester.eu](http://www.koester.eu)**