



Issued: 2018-08-07

KÖSTER TPO 2.0 F W

EPD-KBC-20160014-IBC1-DE Environmental Product Declaration according to the ISO 14025 and EN 15804

Official Test Report according to 1200/372/15 DIN EN 13956 MPA Braunschweig, Official Test Report according to 5278/015/14 DIN EN 13967 MPA Braunschweig, Certificate of conformity of the factory production control 0761-CPR-0422 MPA Braunschweig, Fish test A14-02548 BMG Zürich, Official Test Report acccording to ETAG 006 4/2015 I.F.I. Aachen, Report SRI P15-104/2 Fraunhofer IBF

White TPO Roofing and Waterproofing membrane with central glass fleece insert and an additional polyester fleece backing with high SRI value (106)

100

Features

- Plastic waterproofing membrane made of high quality thermoplastic polyolefins based on polyethylene

- high SRI value of 106 (Solar Reflectance Index)
- central glass fleece insert
- Polyester fleece backside
- uniform material quality (no difference between upper and lower side)
- homogeneous seam bonding with hot air welding
- temperature and weather resistant
- aging and rot resistant
- high cold flexibility (≤ -50°C)
- UV-stable
- root resistant
- compatible with bitumen
- compatible with polystyrene
- suitable for all types of insulation
- resistant against normal mechanical stresses
- resistant to microorganisms and rodent attack
- environmentally friendly
- free of softeners and chlorine
- safe for health, water, soil, and plants
- high SRI value of 106 (Solar Reflectance Index)

Technical Data

Refer to last page

Fields of Application

KÖSTER TPO Roofing and Waterproofing Membranes are used to waterproof unventilated and ventilated flat roofs, pitched roofs, green roofs, terraces, balconies, roof gardens and underground garages with ballast and in cases of direct exposure to weathering. KÖSTER TPO Roofing and Waterproofing Membranes can be used for the waterproofing of basements, wet rooms and tanks.

Application

Please refer to the TPO Installation Instructions and the Technical Manual for TPO of KÖSTER BAUCHEMIE AG for correct application of KÖSTER TPO Roofing and Waterproofing Membranes.

Packaging

RT 820 150 F W	2.0 mm x 1.50 m x 20 m
Related products	
KÖSTER PUR Membrane Adhe	sive Prod. code RT 101
KÖSTER TPO 2.0 W	Prod. code RT 820 W
KÖOTER R. K. R. K. K. K.	

KÖSTER TPO 2.0 W	Prod. code RT 820 W
KÖSTER Roof Drain Vertical DN 125	Prod. code RT 914 001 S
KÖSTER Roof Drain Angled DN 70	Prod. code RT 914 002 A
KÖSTER Universal Roof Drain Extension	Prod. code RT 914 003 A
for roof drain without TPO-seal	

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

KÖSTER System Roof Vent DN 100 KÖSTER Base for System Roof Vent DN Prod. code RT 915 005

Prod. code BT 915 004

Technical Data Sheet RT 820 F W

KÖSTER System Roof Vent Extension for Prod. code RT 915 006 Insulation



	KÖSTER BAUCHEMIE AG
	Dieselstraße 1-10, 26607 Aurich
	KÖSTER TPO 2.0 F W
	EN 13956 0761-CPR-0422
0761	Polyolefin based waterproofing membrane with centrally embedded
15	glass fiber mesh and fleece laminated underside
Length according to DIN EN 1848-2	20 m ¹)
Width according to DIN EN 1848-2	1.50
Effective thickness according to DIN EN 1849-2	2.0 mm
Total thickness DIN EN 1849-2	2.8 mm
	DIN EN 13956: 2012 waterproofing of flat and sloped roofs. Application by loose laying with ballast, mechanical fastening, full surface or strip adhesion
Designation according DIN SPEC 20000-201	DE/E1-FPO-BV-E-GV-2,0
Color	white (SRI 106)
Visible Defects according to DIN EN 1850-2	free from visible defects
Straightness according to DIN EN 1848-2	\leq 50 mm
Flatness according to DIN EN 1848-2	≤ 10 mm
Mass per unit area according to DIN EN 1849-2	2215 g/m^2
Water tightness according to DIN EN 1928 (Method B)	400 kPa/72h watertight
Exposure to liquid chemicals, including water according to	passed (Method B)
DIN EN 1847	
Exposure to external fire according to DIN CEN/TS 1187; DIN 4102-7; DIN EN 13501-5	$B_{roof}(t1); B_{roof}(t4)^{2}$
Reaction to fire	Class E
Resistance to hail according to DIN EN 13583	
Rigid substrate	≥ 25 m/s
Soft substrate	≥ 43 m/s
Peel resistance of the overlap according to DIN EN 12316-2	> 500 N/50mm
Shear resistance of the overlap according to DIN EN 12317-2	Failure beyond the overlap
Water vapor diffusion resistance according to DIN EN 1931 Tensile characterisitcs according to DIN EN 12311-2	μ = 85,000
Tensile strength	≥ 1000 N/50 mm (Method A)
Elongation at break	\geq 50 % (Method A)
Resistance to shock loads according to DIN EN 12691	
Method A	≥ 700 mm
Method B	≥ 1500 mm
Resistance to static loading according to DIN EN 12730 Method A	≥ 20 kg
Method B	≥ 20 kg
Tear continuation resistance according to DIN EN 12310-2	≥ 350 N
Root penetration resistance ⁴⁾	given
Dimensional stability according to DIN EN 1107-2	≤ 0.2 %
Folding at low temperatures	≤ - 50°C
according to DIN EN 495-5	
Behavior under UV irradiation, elevated temperatures, and	passed: Level 0
water according to DIN EN 1297 (1000 h)	
Ozone resistance according to DIN EN 1844	passed
Exposure to bitumen according to DIN EN 1548	passed
Durabilty against heat storage according to DIN EN 1296, DIN EN 1928 (Method A)	watertight
Tear resistance (nail shank) according to DIN EN 12310-1	≥ 500 N
	or roofs tested by KÖSTER. Further information can be requested from KÖSTER.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

R - Roofing membranes, roof waterproofing

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.